

Elastollan® 1192 A10 FHF

Marketing Card



Target Application – Jacketing for wire and cables

Key Selling Points

Suitable for **VW-1** and **FT-1** cables.

Halogen-free flame retardant

Hydrolysis and micro-organisms resistance, **low temperature flexibility** (-40°C)

Best End-Use Markets and Applications

Consumer Electronics Automotive EV Charging Industrial Drag Cables

Certification and Standards

UL94 V-0 at 0.8 and 3.2 mm jacket thickness

REACH, RoHS and IMDS

Offset Guide

Lubrizol Estane® 58202, 58370, ZHF 95AT and ZHF 92AT

Pricing and Availability

 – see Price List.

Sample material is available

Due to high demand, forecast recommended for commercial volumes.

General Product Information

Property	Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183-1-a
Hardness	91	Shore A	DIN ISO 7519-1 (3s)
Tensile strength	17	MPa	DIN 53504-S2
Elongation at break	550	%	DIN 53504-S2
Tear strength	55	N/mm	DIN ISO 34-1Bb
Abrasion loss	80	mm ³	DIN ISO 4649-A
Change of Tensile Strength after 7d air aging at 113°C	8	%	DIN 53504-S2
Change of Elongation at break after 7d air aging at 113°C	-7	%	DIN 53504-S2

Flat films (thickness 1,6mm) are manufactured by extrusion from pre-dried granules (water content less 0,02%). The flat films are aged 20 hrs at 100°C. Specimens are cut from flat films. Test conditions: 23°C ± 2°C and 50% ± 6% rel. humidity.

Flammability and Smoke Density/Toxicity

Property	Value	Unit	Test Method
Flammability (UL94-V)	V-0	0.8, 3.2 mm	UL94 - V
Conventional Toxicity Index (smoke gas toxicity)	44.1	ITC at 600°C	NFX 70-100, Parts 1+2: 2006-04
Smoke Density Flaming mode	205	Ds max.	NF X 10-702, Part 1: 1995-11
Acidity of gases during combustion	8.1	pH - value	DIN EN 50267-2-2: 1999
	56.4	Conductivity (µS/mm)	
Determination of burning behaviour by oxygen index	29	LOI - Limiting Oxygen Index [%]*	ISO 4589 Part2: 2006-06)

(1) Same cable construction * measured by 1.6mm film

Rolling Stock Applications - Fire Protection on Railway Vehicles DIN EN 45545-2 (2013-08) R22/R23

Property	Value	Unit	Test Method
Smoke Density	205*	Ds max.	EN ISO 5659-2: 25 kWm ⁻²
Toxicity	0.5	CIT _{NLP}	NF X70-100-1 and -2
Oxygen Volume (%)	29	%	EN ISO 4589-2: OI
Rating R22/R23	HL2/HL2	--	--

*screening test for smoke density

BASF Contact:

Christopher A. Bradlee
 Market Development Manager - Performance Materials
 Phone: +1 (734) 324-6867 Mobile: +1 (734) 512-3527
 Email: christopher.bradlee@basf.com

THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH, AND ARE BASED ON BASF'S CURRENT KNOWLEDGE AND EXPERIENCE. THEY ARE PROVIDED FOR GUIDANCE ONLY, AND DO NOT CONSTITUTE THE AGREED CONTRACTUAL QUALITY OF THE PRODUCT OR A PART OF BASF'S TERMS AND CONDITIONS OF SALE. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE OF THE PRODUCT, BASF RECOMMENDS THAT THE READER CARRY OUT ITS OWN INVESTIGATIONS AND TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR ITS PARTICULAR PURPOSE PRIOR TO USE. IT IS THE RESPONSIBILITY OF THE RECIPIENT OF PRODUCT TO ENSURE THAT ANY PROPRIETARY RIGHTS AND EXISTING LAWS AND LEGISLATION ARE OBSERVED. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH HEREIN, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** ANY DESCRIPTIONS, DESIGNS, DATA AND INFORMATION GIVEN IN THIS PUBLICATION MAY CHANGE WITHOUT PRIOR INFORMATION. THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

© 2016, Wyandotte, MI 48192

® = registered trademark of BASF Corporation